

内部酸化法（後酸化方式）材質詳細 [一般例]

種類	材質	Ag (Wt%)	その他 (Wt%)	硬度 (Hv)	導電率 (IACS%)
● Cdフリー材					
Ag-SnO ₂ -In ₂ O ₃	M2-1	89	11	105	60
	M2	84	16	110	47
	M2-1/2	90	10	95	62
	M2-J	86	14	110	55
	NEOTACT-B	84	16	115	55
	NEOTACT-D	86.3	13.7	115	55
Ag-In ₂ O ₃ -SnO ₂	M1	85	15	100	52
Ag-SnO ₂	ST-C	92	8	95	77
● Cd材					
Ag-CdO	TOB-2	86	14	(HRF)45	70
Ag-CdO- α	TOFM-5N	81	19	90	55
	BH	79	21	105	55
Ag-CdO- α	CM-N	81	19	100	60