

## 交流用(AC)リレー向け材質詳細 [一般例]

種類	材質	Ag (Wt%)	その他 (Wt%)	硬度 (Hv)	導電率 (IACS%)
GS	GS	90	10	29	48
PGS	PGS	25	75	60	11
PdRu	PdRu	90	10	160	4.6
AgPd	AgPd	70	30	87	12

種類	材質	Ag (Wt%)	その他 (Wt%)	硬度 (Hv)	導電率 (IACS%)
<b>● Cdフリー材</b>					
Ag-SnO <sub>2</sub> -In <sub>2</sub> O <sub>3</sub>	M2X-1	89	11	105	75
	M2X-J	86	14	110	70
	M2X-1/3	92	8	95	80
	M2X-1/4	94	6	95	85
	NEOTACT-BX	84	16	115	65
	NEOTACT-DX	86.3	13.7	115	70
Ag-SnO <sub>2</sub>	STANOX-CX	92	8	100	85
Ag-ZnO	NEOTACT-ZX	91	9	100	85
Ag-Ni	AgNi10	90	10	90	95
	AgNi15	85	15	90	90
	AgNi20	80	20	95	85
<b>● Cd材</b>					
Ag-CdO	TOFX-2	87	13	95	75
Ag-CdO- $\alpha$	CMX	81	19	100	60